APPLICANT(S): BARTLETT, Philip Nigel et al.

SERIAL NO.: 10/538,771

FILED: December 12, 2007

Page 2

AMENDMENTS TO THE CLAIMS

Please amend claims 1, 4-7, 9, 15 and 16 to read as follows

The listing of claims below will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

(Currently Amended) An electrochemical cell comprising a cathode, an anode and an
electrolyte, wherein,

said cathode comprises a mesoporous structure comprising mesoporous nickel comprising a periodic arrangement of substantially uniformly sized pores of cross-section in the order of 10^{-9} to 10^{-8} m; and

said anode comprises <u>a mesoporous structure comprising</u> a mesoporous material having a periodic arrangement of substantially uniformly sized pores of cross-section in the order of 10^{-9} to 10^{-8} m, said anode made of carbon, cadmium, iron, a palladium/nickel alloy, an iron/titanium alloy, palladium or a mixed metal hydride.

- 2. (Previously Presented) An electrochemical cell according to claim 1, wherein said mesoporous structure of said cathode comprises nickel and an oxide, hydroxide or oxy-hydroxide of nickel selected from NiO, Ni(OH)₂ and NiOOH, said nickel oxide, hydroxide or oxy-hydroxide forming a surface layer over said nickel and extending over the pore surfaces.
- (Previously Presented) An electrochemical cell according to claim 1, wherein said mesoporous structure of said cathode is comprised of nickel or alloys of nickel.
- (Currently Amended) An electrochemical cell according to claim 1, wherein said mesoporous structure of <u>said cathode or of said anode or both</u> has a pore diameter in the range of about 1 to about 10 nm.

APPLICANT(S): BARTLETT, Philip Nigel et al.

SERIAL NO.: 10/538,771

FILED: December 12, 2007

Page 3

(Currently Amended) An electrochemical cell according to claim 1, wherein said
mesoporous structure of said cathode or of said anode or both has a pore number density from
about 4x10¹¹ to about 3x10¹³ pores per cm².

- 6. (Currently Amended) An electrochemical cell according to claim 1, wherein at least 85 % of the pores in said mesoporous structure of said cathode or of said anode or both have pore diameters within 30 % of the average pore diameter.
- (Currently Amended) An electrochemical cell according to claim 1, wherein said
 mesoporous structure of said cathode or of said anode or both has a hexagonal arrangement
 of pores that are continuous through the thickness of the electrode.
- (Previously Presented) An electrochemical cell according to claim 7, wherein said hexagonal arrangement of pores has a pore periodicity in the range of 5 to 9 nm.
- (Currently Amended) An electrochemical cell according to claim 1, wherein said
 mesoporous structure of said cathode or of said anode or both is a film having a thickness in
 the range of about 0.5 to about 5 micrometers.
- (Previously Presented) An electrochemical cell according to claim 1, wherein said anode comprises carbon or palladium.
- 11. (Previously Presented) An electrochemical cell according to claim 1, wherein said mesoporous structure of said cathode comprises nickel and an oxide, hydroxide or oxyhydroxide of nickel, forming a surface layer over said nickel and extending over at least the pore surfaces, and wherein said anode has a mesoporous structure comprising carbon or palladium.
- 12. (Previously Presented) An electrochemical cell according to claim 3, wherein said nickel alloys are nickel alloys with a transition metal, nickel/cobalt alloys or iron/nickel alloys.

APPLICANT(S): BARTLETT, Philip Nigel et al.

SERIAL NO.: 10/538,771

FILED:

December 12, 2007

Page 4

 (Previously Presented) An electrochemical cell according to claim 4, wherein said pore diameter is in the range of about 2.0 to about 8.0 nm.

- 14. (Previously Presented) An electrochemical cell according to claim 5, wherein said pore number density is in the range of about 1x10¹² to about 1x10¹³ pores per cm².
- 15. (Currently Amended) An electrochemical cell according to claim 6, wherein at least 85 % of the pores of said cathode or of said anode or both have pore diameters within 10% of the average pore diameter.
- 16. (Currently Amended) An electrochemical cell according to claim 6, wherein at least 85 % of the pores of said cathode or of said anode or both have pore diameters within 5% of the average pore diameter.
- (Previously Presented) An electrochemical cell according to claim 11, wherein said oxide, hydroxide or oxy-hydroxide of nickel is NiO, Ni(OH)₂ or NiOOH.